

PRODUCT SPECIFICATION

Screencare UV windscreen repair resin

LIQUID PROPERTIES

One part U.V adhesive	
Appearance	Clear, colourless
Flashpoint	> 100°C
Density	1,0682 (g/cm ³)
Shelf Life	12months, unopened
Viscosity Brookfield @ 25°C, spindle 3	25 @ 20rpm, 18 @ 50rpm

POLYMER PROPERTIES

Appearance	Clear, colourless
Refractive Index,	1,4512 @ 25°C
Full Cure Time	60 – 120 seconds

CURED PERFORMANCE

Cure Speed (using 125 watt mercury vapour lamp @ 2cm)

Initial Cure	30 – 60 seconds
Full cure	60 – 120 seconds

Shear strength and tensile strength T.B.A

PRODUCT STORAGE

Store upright in original, unopened containers in a cool, dry well ventilated place at temperatures between 5 and 25°C. Protect from heat and sunlight. Refrigeration may prolong shelf-life.